



TG-P100 Series Graphene

RoHS Compliant

Features

- Ultra thin, Low mass
- Available for unventilated design
- No dusting issue

Applications

Suitable for products requiring flat temperature

Electronic components - Electric Vehicles, 5G, Autopilot System, Mobile Phone, AIOT, HPC (High Performance Computing), Server, IC, CPU, MOS, LED, Mother Board, Power Supply, Heat Sink, LCD-TV, Notebook, PC, Telecom Device, Wireless Hub, DDR II Module, etc.

Properties

Properties	TG-P10050	TG-P10090	Unit	Tolerance	Test Method
Thermal Conductivity (XY axis)	1500~1800		W/mK	-	AC calorimeter
Thermal Conductivity (Z axis)	12		W/mK	-	Laser flash
Total Thickness	50	90	µm	-	Meter
Copper Foil Thickness	35	75	µm	-	Meter
Coating Thickness	15	15	µm	-	Meter
Vertical Resistivity (XY axis)	2.57		KV/mm	-	QJ1523-1988
Parallel Resistivity (Z axis)	0.66		KV/mm	-	QJ1523-1988
Cross-cut Tape Test	4B		-	-	ASTM D3359B
Pencil Hardness Test	2H		-	-	ASTM D3363
Solvent Resistance (Alcohol)	Pass(5 times)		° C	-	ASTM D5402
Rubber Abrasive Test	Pass(150 times)		Ohm-m	-	ASTM D7835
High Temperature & Humidity Test @85° C/85%RH	Pass(500hrs)		-	-	IEC-60068-2-78
Thermal Shock Test @-20~+80° C	Pass(500cycles)		-	-	IEC-60068-2-14
Temperature Range of Utility	-20~+120		° C	-	ISO 16750-4

Pre-cut for different shapes

T-Global Technology (Europe & North America) Limited

Units 1-2 Cosford Business Park, Central Park, Lutterworth, Leicestershire, LE17 4QU, United Kingdom
T +44 (0)1455 553 510 **E** sales@tglobaltechnology.com **W** www.tglobaltechnology.com

Version17
20200501



T-Global Technology are proud to announce the launch of a new company logo and mission statement as part of the ongoing growth and evolution of our company's brand.

NOTICE: The information contained herein is to the best of our knowledge true and accurate. Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. All specifications are subject to change without notice. The protective film does not affect the function of the product. If there is no special requirement, the default depends on T-Global. Since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.